



Research Article

HIGHLY ACTIVE TiO₂ NANOPHOTOCATALYSTS FOR DEGRADATION OF METHYL ORANGE UNDER UV IRRADIATION

Hiral Soni¹, Nirmal Kumar J. I.¹, Khushal Patel², Rita N. Kumar³

¹P.G. Department of Environment Science and Technology (DEST), Institute of Science and Technology for Advanced Studies and Research (ISTAR), Vallabh Vidyanagar -388120 (Gujarat), India

²Ashok and Rita Patel Institute of Integrated Study and Research in Biotechnology and Allied Sciences, New Vallabh Vidyanagar-3888121 (Gujarat), India

³Department of Bioscience & Environment Science, N.V.Patel college of Pure and applied sciences, Vallabh Vidyanagar -388120 (Gujarat) India

Correspondence should be addressed to **Hiral Soni**

Received March 10, 2015; Accepted March 21, 2015; Published March 23, 2015;

Copyright: © 2015 **Hiral Soni** et al. This is an open access article distributed under the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Cite This Article: Soni, H., Kumar J. I., N., Patel, K., N. Kumar, R. (2015). Highly active TiO₂ nanophotocatalysts for degradation of Methyl Orange under UV irradiation. International Journal of Earth & Environmental Sciences, 1(1). 1-8

ABSTRACT

This study describes the application of novel chemistry methods for the removal of dye by Nano structured titanium oxide (TiO₂) photo catalysts. Such materials can be applied in the development of efficient photo catalytic systems for the treatment of water. Nano crystalline TiO₂ was synthesized by Sol-Gel route using titanium tetraisopropoxide as a metal precursor. The catalysts were characterized by X-ray diffraction (XRD), Transmission Electron Microscopy (TEM), Fourier-transform infrared spectroscopy (FT-IR). Synthesized TiO₂ was related to anatase phase and crystalline structure was characterized by XRD. Cuboidal and uneven shape of TiO₂ nanoparticles were observed by TEM images. FTIR reveals the functional groups present in the synthesized TiO₂ nanoparticles. Thus synthesized TiO₂ nanoparticle was used for photo catalytic degradation of methyl orange. The photo degradation of methyl orange (MO) dye, is examined both under different dye concentration (10, 20, 30 and 40 ppm) and amounts of TiO₂ (5, 10, 15 and 20 mg / 10 ml). After 15W UV-365 nm irradiation for 3 h, ca. 99.9% of MO was degraded with addition of 20mg TiO₂ to solutions containing 40ppm dye. The photo degradation mechanism of the quinonoidal methyl orange using nanoparticles is low cost, eco-friendly and cost effective process in the removal of toxic dyes.

KEY WORDS: TiO₂ nanoparticles, Photo catalytic degradation, Methyl Orange, XRD, TEM, FTIR.

INTRODUCTION

Paper, dyeing, plastic and textile industries use color for dyeing their products and thus use a huge amount of water which results in the production of a dye-containing wastewater with hazardous effects on the environment [1][2][3][4]. At present, 100000 different types of dyes with annual production rate of 7410⁵ are produced. Among

them textile industries consume about 36000 ton/year dye, 10 to 20 percent of which remains in wastewater [5]. The presence of these dye pollutants in water streams causes numerous problems related to their carcinogenicity, toxicity to aquatic life and easily detected and undesirable esthetic aspect [6]. Dyeing effluents are very difficult to treat, due to their resistance to biodegradability, stability to light, heat and oxidizing agents [7]. MO causes eye and skin irritation and may cause respiratory and digestive tract irritations and it is also responsible for toxic effects. In

addition to standard technologies for the degradation and/or removal of dyes, several new specific technologies, the so-called advanced oxidation processes (AOPs), have been developed. Heterogeneous photo catalysis, as one of the AOPs, could be effective in the oxidation /degradation of organic dyes. The initial interest in the heterogeneous photo catalysis was aroused in 1972 when Fujishima and Honda discovered the photochemical splitting of water into hydrogen and oxygen by the UV irradiated TiO₂ [8]. After that, research on the heterogeneous photo catalysis started growing rapidly [9] in many area covering water and air treatment technologies.

Among the metal oxide semiconductors, TiO₂ is widely used catalyst because of its fascinating physicochemical properties, high photo activity, photo-corrosion stability, nontoxic and low cost [10][11]. It finds its application as solar cells, gas sensors, photo catalysts, capacitors, and catalyst supports [12][13][14][15][16]. TiO₂ self-cleaning property can be bestowed on many different types of surface, and some TiO₂ based self-cleaning products such as tiles, glass, and plastics have been commercially available. TiO₂ self-cleaning coatings are finding increasing applications in buildings, public furniture and auto industry. The self-cleaning mechanism is mainly based on TiO₂ photo catalysis, where photo-induced electron-holes catalyze reaction on the surface [17][18]. The electrons and holes form hydroxyl radicals which are assumed to be the main reactants in the degradation of many pollutants like herbicides [19], fungicide [20], aliphatics and aromatics [21], dyes [22] and bacteria [23]. TiO₂ has many polymorphs, among which anatase TiO₂ shows the highest photo catalytic activity toward photo degradation of most organic pollutants in waste water.


In this case, photosensitization of the dye may occur upon excitation by UV-light in addition to the hydroxyl radical attacking the dye molecules. The photo generated electrons might also transfer from the excited dye to the semiconductor particle. It can also reduce the adsorbed oxygen in the suspensions to form superoxide radicals, than the reaction between the dye radical and the other active oxygen-containing species might also occur, which can accelerate the photo degradation process of the dye [24]. In the present investigation, TiO₂ nanoparticles were synthesized via Sol-Gel route using Titanium Tetraisopropoxide as a metal precursor and was characterized by X-ray diffraction (XRD), Fourier-transform infrared absorption spectrophotometry (FT-IR), Transmission Electron Microscopy (TEM), moreover, water pollutant substance from industry, one of the dyes, methyl orange was studied in aqueous medium for photo catalytic degradation under irradiation of ultraviolet light.

METHODOLOGY

Materials

Titanium Tetraisopropoxide (97%) was provided by Sigma Aldrich Co, 3050, St.Louis, MO, USA, Glacial Acetic Acid (99%) was purchased from Hi-Media. Methyl Orange was of analytical reagent grade and used without further purification. All solutions used in the experiments were prepared by using double distilled demineralised water. The chemical structure, IUPAC name, molecular weight and Colour Index (CI) number of Methyl Orange is represented in Table 1.

Table 1: Structure and characteristics of malachite green

Dye	Methyl Orange
Structure	
λ_{max}	463nm
IUPAC name	Sodium 4-[(4-dimethylamino)phenyl]diazenylbenzenesulfonate
M _w	327.33 g/mol
C.I. number	13025

Catalyst Preparation

The Sample was prepared by novel and simple Sol-Gel route. 12 mL titanium isopropoxide was added to 23 mL acetic acid with continuous stirring. Hydrolysis of titanium tetraisopropoxide solution was carried out by adding distilled water (72 ml) slowly at the rate of 0.5 ml/min with continuous stirring. The solution was kept stirring for 6 h until achieving a clear transparent sol. Dried at 100°C, after that it was calcined at 600°C for 2 h at a ramp rate of 5°C/min. [25].

Catalytic characterization

Powder XRD patterns were recorded with a Phillips X'pert MPD system, Holland using CuK α radiation ($\lambda=1.5405$ Å) in a 2θ range of 5–60 $^\circ$ at a scan speed of 0.11 s $^{-1}$ and patterns were compared with the standard anatase diffractograms [26]. Transmission Electron Microscope (TEM) studies were carried out on the sample using a model Philips Tecnai 20, Holland with an accelerating voltage of 100kV for the details of size, and morphological structure. An FT-IR spectrophotometer (SPECTRUM GX, Perkin- Elmer) was used to determine the specific functional groups in TiO $_2$ samples. The spectrum is recorded in the range of wave-number 400–4,000 cm $^{-1}$.

Photo catalytic experiment

The photo catalytic activities of the materials were studied by examining the degradation reactions [27]. Methyl Orange stock containing four different concentration of dye i.e. 10ppm,20ppm,30ppm,40ppm were prepared in borosilicate glass tubes containing various doses of synthesized catalytic TiO $_2$ nanoparticles. Catalysts containing tubes were placed on UV- radiation lamp. Two 15 W low pressure mercury UV tubes (Spectronics) emitting near UV radiation with a peak at 365 nm were used at a light intensity of 3.48 mW/cm 2 measured near the film surface. The photo catalytic oxidation process started when UV radiation reached the TiO $_2$ photo catalyst. Afterwards at one hour time interval sample were collected, centrifuged and analyzed with a UV-Vis spectrophotometer. A blank study was also carried out only in the presence of UV light without any catalyst. This shows that though during UV irradiation, direct photolysis of dyes could occur, mineralization of dyes only takes place in the presence of a photo catalyst [28]. In the photo degradation experiments the extent of removal of the dye, in terms of the values of percentage removal has been calculated using the following relationship:

Equation 1

$$\text{Percentage Removal (\%R)} = 100 \cdot (C_i - C_f) / C_i \quad (1)$$

Where, C_i = initial concentration of dye (ppm); C_f = final concentration of dye (ppm) at given time.

RESULTS AND DISCUSSION

Crystallinity and crystallite size

The photo catalytic activity of catalyst was greatly affected by its crystal structure and crystal phase. The crystal structure and crystal phase characterization of pure TiO $_2$ is investigated. Generally, the anatase phase is reported with high photo catalytic activity than Rutile. The XRD patterns of samples are shown in Figure 1. In TiO $_2$ sample in the present investigation, Anatase phase was detected. The average crystalline size calculated by applying the Scherrer formula on the anatase diffraction peak at $2\theta = 25.28^\circ$ (101), $2\theta = 37.74^\circ$ (004), $2\theta = 48.08^\circ$ (200), $2\theta = 53.93^\circ$ (105) and $2\theta = 62.79^\circ$ (204). The preferred orientation corresponding to the plane (101) is observed in the sample. All the peaks in the XRD patterns can be indexed as anatase phases of TiO $_2$ and the diffraction data were in good agreement with JCPDS files # 21-1272 [29]. It should be noted that only Anatase TiO $_2$ is detected and no Rutile phase can be found in the sample [30]. Crystallite size was also obtained by Debye-Scherrer's formula given by equation


Equation 2

$$D = K\lambda / (\beta \cos\theta)$$

Where D is the crystal size; λ is the wavelength of the X-ray radiation ($\lambda=0.15406$ nm) for CuK α ; K is usually taken as 0.89; and β is the line width at half-maximum height [31]. The relatively wide width of the peaks indicates small crystallite size, which was estimated to be approximately 24 nm using Scherrer's equation from the XRD peak broadening analysis at (1 0 1) [32]. It is worth to note that the crystallite size was in the range of 20–30 nm, which is known to be optimum for high catalytic activity. This is because a very small crystallite size causes a blue shift in the light absorption spectrum and favours surface recombination of the photo-excited holes and electrons while a larger crystallite size exhibits lower surface area and thus a smaller number of catalytic active sites per unit mass of catalyst [33].




Figure 1 XRD powder pattern of synthesized TiO_2 by Sol-Gel



Functional Group analysis of TiO_2 nanoparticles

Fourier transform infrared (FTIR) spectrum of as-synthesized anatase TiO_2 nanoparticles is shown in Figure 2. It was observed that the strong band in the range of 700–500 cm^{-1} is associated with the characteristic vibration modes of TiO_2 . This confirms that the TiO_2 phase has been formed. The absorption in the range from 3,500 to 2,500 cm^{-1} may be related to the presence of O–H stretching vibration (Monomer, intermolecular, intra molecular and polymeric) [34]. The absorption band at 1,637 cm^{-1} due to the presence of O–H bending vibration which is probably because of the reabsorption of water from the atmosphere has occurred [35].


Figure 2: FTIR spectra of synthesized TiO_2



Structural characteristics of TiO₂ nanoparticles

The above results indicated that the precursor titanate obtained was in nanostructure, which is further confirmed by TEM observation. The homogeneity, uniformity and the size of the resulting TiO₂ crystals were studied by TEM, as shown in Figure 2. TEM study indicated that all the crystals were completely separated from each other and uniformed with a particle analytical grade with size of 20 -30 nm. These particles do not grow together to form bigger particles, even after an extensive period of time. It is worth noting that only a small percentage of the total particles exhibit a diameter size bigger than 30 nm. The crystallites had sets of clearly resolved lattice fringes giving evidence that the TiO₂ material was highly crystalline [36].

Figure 3: TEM image of synthesized TiO₂ nanoparticles



However, there was a slight discrepancy between the particles sizes determined by XRD analysis and TEM. This could be due to the fact that the effective mass approximation is relatively less correct for small nanoparticles and statistical effects of spatial confinement also influence the optical properties of Nano crystalline semiconductors [37].

De colorization efficiency of UV/TiO₂ photo catalysis process

Photo catalytic properties of the as-prepared samples were examined by degradation of MO dye solution under UV light irradiation at room temperature. In order to identify possible losses of methyl orange in the system, control experiments without catalyst added were preformed. The course of methyl orange photo catalytic degradation used pure catalyst TiO₂ at different amount added to different dye concentration. It was found that no obvious methyl orange loss was observed in control experiment which confirmed that the methyl orange was stable in our experiment. However, four dye concentrations- 10ppm, 20ppm, 30ppm, 40ppm were irradiated with different catalytic doses of 5mg, 10mg, 15mg and 20mg. At 20mg catalytic dye was found to be almost completely decolourised on irradiation for 120 minutes. Catalyst loading of 20mg showed better result than other 3 doses (Figure 4). For 30 and 40 ppm, about 60% degradation was obtained within 1 hour for 20mg concentrations of catalyst. However, 99% degradation was obtained for catalyst loading of 20mg at 3 hours (Figure 5). The degradation increases with increase in catalytic dose. There is no doubt that electron injection from the dye to the positive holes of TiO₂ yields the dye cationic radical. After this stage, the cationic radical, Dye^{•+}, can undergo hydrolysis and/or de protonation pathway of the dye cationic radicals, which in turn are determined by the different adsorption modes of MO on the TiO₂ particles surface[38]. Total mineralization of the organic dye pollutants usually follows proposed mechanism described below [39][40].

Percentage de coloration vs. Dose of TiO₂nanoparticles at 10ppm and 20ppm MO




Figure 4




Figure 5






Figure 6






Figure 7

Photo catalysis occurs by following proposed mechanism given in step wise manner.


- i. Absorption of efficient photons ($h\nu \geq EG = 3.2 \text{ eV}$) by titania



- ii. Oxygen ionosorption (first step of oxygen reduction; oxygen's oxidation degree passes from 0 to $-1/2$)




- iii. Neutralization of OH^- groups by photo holes which produces OH^\bullet radicals




- iv. Neutralization of $\text{O}_2^{\bullet-}$ by protons



- v. Transient hydrogen peroxide formation and dismutation of oxygen



- vi. Decomposition of H_2O_2 and second reduction of oxygen



- vii. Oxidation of the organic reactant via successive attacks by OH^\bullet radicals



- viii. Direct oxidation by reaction with holes



- ix. As an example of the last process, holes can react directly with carboxylic acids generating CO_2



Increase in the concentration of catalyst shows an increase in dye degradation for the first few minutes. This is due to the fact that number of dye molecules adsorbed and photon absorbed increases with increase in catalyst loading. The increase in degradation was probably due to an increase in availability of catalytic sites and adsorption sites. It could be due to decolorization of MO which undergone demethylation, methylation and hydroxylation processes.

CONCLUSION

In this research, A novel, easy and reproductive method was followed for the synthesis of TiO_2 and photo catalytic activity of TiO_2 nanoparticles on Methyl Orange was studied. It's physical and chemical characterization was done by TEM, XRD and FT-IR. The obtained results comply with that of standard. The ultraviolet (UV) light irradiation of the dye by using nanoanatase TiO_2 as a catalyst has yielded percentage decolouration of greater than 90% for a catalyst loading of 20mg and initial concentration of the dye solution of 10-40ppm.

ACKNOWLEDGEMENT

The authors would like to thank Sophisticated Instrumentation Centre for Advanced Research and Testing (SICART), Vallabh Vidyanagar, Gujarat, for analysis of samples .

REFERENCES

- [1] H. Lachheb, E.Puzenat, A.Houas, M.Ksibi, Photocatalytic degradation of various types of dyes in water by UV- irradiated titania, Appl. Catal. B: Env., Vol. 39, (2002),pp. 75-90.
- [2] C. Gregorio, Non-conventional low-cost adsorbents to dye removal, Bioresour. Technol., Vol. 97, (2006),1061 -1085.
- [3] S.Sreedhar,B. Kotaiah, Comparative evaluation of commercial and sewage sludge based activated carbons for the removal of textile dyes from aqueous

- solutions, *Iran. J. Env. Health Sci. Eng.*, Vol. 3, (2006),pp. 239-246.
- [4] G.N. Bidhendi, A.Torabian, H.Ehsani, N.Razmkhah, Evaluation of industrial dyeing wastewater treatment with coagulants and polyelectrolyte as a coagulant aid, *Iran J Sci Technol*, Vol. 4,(2007), 29-36.
- [5] S.J. Espulgas, S. Gimenez, E.P.Contreras, M. Rodriguez, Comparison of Different Advanced Oxidation Processes for Phenol Degradation, *Water Res.*, Vol. 36, (2002),pp. 1034-1042.
- [6] A.R.Khataee, V.Vantanpour, A.R. Amani, Decolorization of C.I. Acid Blue 9 solution by UV/nano-TiO₂, Fenton, Fenton-like, electro-Fenton and electrocoagulation processes: a comparative study, *J. Hazard. Mater.*, Vol. 161, (2009),pp. 1225-1233.
- [7] A.R. Khataee, O. Mirzajani, UV/peroxydisulfate oxidation of C.I. Basic Blue 3: modeling of key factors by artificial neural network, *Desalination*, Vol. 251, (2010), pp.64-69.
- [8] A.Fujishima, X. Zhang, D.A.Tryk, TiO₂ photocatalysis and related surface phenomena, *Surf. Sci. Rep.*, Vol.63, (2008),pp.515-582.
- [9] A .Fujishima, X. Zhang, D.A. Tryk Titanium dioxide photocatalysis: present situation and future approaches, *J. Photochem. Photobiol. C: Photochemistry*, Vol. 1, (2000),pp. 1-21.
- [10] A.L.Linsebigler, G.Q. Lu, J.T. Yates, Photocatalysis on TiO₂ surfaces: principles, mechanisms, and selected results, *Chem. Rev.*, Vol. 95, (1995),pp. 735-758.
- [11] M.R. Hoffman, S.T.Martin, W.Choi, W.Bahnmann, Environmental applications of semiconductor photocatalysis, *Chem. Rev.*, Vol. 95, (1995),pp. 69-96.
- [12] B .O'Regan, M. Gratzel, A low-cost high-efficiency solar cell based on dye-sensitized colloidal TiO₂ films, *Nature*, Vol. 353, (1991),pp.737-740.
- [13] T.N.Murakami, N.Kawashima, T.Miyasaka, A high-voltage dye-sensitized photocapacitor of a three-electrode system, *Chem. Commun.*, Vol.26, (2005),pp. 3346-3348.
- [14] E.Palomares, R. Vilar, J.R. Durrant, Heterogeneous colorimetric sensor for mercuric salts, *Chem. Commun*, Vol.4, (2004),pp. 362-363.
- [15] U.G. Akpan, B.H. Hameed, The advancements in sol-gel method of doped-TiO₂ photocatalysts, *Appl. Catal :A* Vol. 375, (2010),pp. 1-11.
- [16] D.R.Park, J.Zhang, K. Ikeue, H.Yamashita, M.Anpo, Photocatalytic Oxidation of Ethylene to CO₂ and H₂O on Ultrafine Powdered TiO₂ Photocatalysts in the Presence of O₂ and H₂O, *J. Catal.*, Vol. 185, (1999),pp.114-119.
- [17] Z.Liu, X.Zhang, T.Murakami, A. Fujishima, Sol-Gel SiO₂/TiO₂ bilayer films with self-cleaning and antireflection properties, *Sol. Energy Mater. Sol. Cells*, Vol. 92, (2008),pp.1434-1438.
- [18] H.Yaghoubi, N.Taghavinia, E. Z.Keshavarz, E. Alamdari, Self cleaning TiO₂ coating on polycarbonate: Surface treatment, photocatalytic and nanomechanical properties, *Surf. Coat. Technol.*, Vol. 204, (2010),pp. 1562-1568.
- [19] F.Fresno, C.Guillard, J.M.Coronado, J.M.Chovelon, D.Tudela, J.Soria, J.M. Herrmann, Photocatalytic degradation of a sulfonylurea herbicide over pure and tin-doped TiO₂ photocatalysts, *J. Photochem. Photobiol., A: Chemistry*, Vol. 173, (2005),pp 13-20.
- [20] A.Danion, J.Disdier, C.Guillard, O.Panssü, N.Jaffrezic-Renault, Photocatalytic degradation of imidazolinone fungicide in TiO₂-coated optical fiber reactor, *Appl. Catal. B: Env*, Vol. 62,(2006), pp. 274-281.
- [21] M.Mrowetz, E.Selli, Photocatalytic degradation of formic and benzoic acids and hydrogen peroxide evolution in TiO₂ and ZnO water suspensions, *J. Photochem. Photobiol., A: Chem.*, Vol.180,(2006), pp.15-22.
- [22] N. Barka, A. Assabane, A. Nounah, A.Y. Ichou, Photocatalytic degradation of indigo carmine in aqueous solution by TiO₂-coated non-woven fibres, *J. Hazard. Mater.*, Vol.152, (2008),pp.1054-1059.
- [23] A.G. Rincyn, C. Pulgarin, Photocatalytical inactivation of E. coli: effect of (continuous-intermittent) light intensity and of (suspended-fixed) TiO₂ concentration, *Appl. Catal : B Env*, Vol. 44,(2003), 263-284.
- [24] P.V.Kamat, Photochemistry on nonreactive and reactive (semiconductor) surfaces, *Chem.Rev.*, Vol.93, (1993), pp. 267-300.
- [25] D.A. Kumar, J.M. Shyla, Synthesis and characterization of TiO₂/ SiO₂ nano composites for solar cell applications, *Applied Nanoscience*, Vol. 2, (2012),pp.429-436.
- [26] C. Chen, C.S .Lu, Y.C.Chung, J.L. Jan, UV light induced photodegradation of malachite green on TiO₂ nanoparticles, *J. Hazard. Mater.*, Vol. 14, (2007) ,pp. 520-528.
- [27] R.J.Tayade, P.K. Surolia, R.G. Kulkarni, R.V.Jasra, Photocatalytic degradation of dyes and organic contaminants in water using nanocrystalline anatase and rutile TiO₂. *Sci. Tech. Adv. Mater.*, Vol. 8, (2007),pp. 455-462.
- [28] M.Pelaez, A.D.L.Cruz, E. Stathatos, P.Falaras, D.D.Dionysiou, Visible light-activated N-F-codoped TiO₂ nanoparticles for the photocatalytic degradation of microcystin-LR in water. *Catal. Today*, Vol.144, (2009), pp.19-25.
- [29] P.K.Khanna, N.Singh, S.Charan, Synthesis of nanoparticles of anatase TiO₂ and preparation of its optical transparent film in PVA, *Mater. Lett*, Vol. 61, (2007), pp.4725-4730.
- [30] S.Qiu, S.J.Kalita, Synthesis, processing and characterization of nanocrystalline titanium dioxide, *Mater. Sci. Eng.A*, Vol. 327, (2006), pp.435-436.
- [31] S. Nakade, M. Matsuda, S. Kambe, Y. Saito, T. Kitamura, T. Sakata, Y. Wada, H. Mori, S. Yanagida, Dependence of TiO₂ Nanoparticle Preparation Methods and Annealing Temperature on the Efficiency of Dye-Sensitized Solar Cells, *J. Phys. Chem. B*, Vol. 106, (2002),pp.10004-10010.
- [32] Z Zhang, C.C. Wang, R. Zakaria, J.Y. Ying, Role of Particle Size in Nanocrystalline TiO₂-based Photocatalyst, *J. Phys. Chem.*, Vol. 102, (1998),pp. 10871-10878.
- [33] H.Choi, E. Stathatos, D.Dionysiou, Sol-gel preparation of mesoporous photocatalytic TiO₂ films and TiO₂/Al₂O₃ composite membranes for environmental applications, *Appl. Catal. B: Env*, Vol. 63, (2006), 60-67.
- [34] S.V.Gaponenko, *Optical Properties of Semiconductor Nanocrystals*, (1998), Cambridge University Press, Cambridge.
- [35] J.Mohan, *Organic spectroscopy principles and applications*, 2nd edn. Narosha Publishing House Pvt. Ltd, New Delhi, (2009),pp. 28-95.
- [36] R.A.Aziz, I. Sopyan, Synthesis of TiO₂-SiO₂ powder and thin film photocatalysts of sol-gel method, *Int. J. Chem.*, Vol. 48,(2009),pp. 951-957.
- [37] G.Liu, X. Li, J. Zhao, H. Hidaka, N. Serpone, Photooxidation pathway of sulforhodamine-B, Dependence on the adsorption mode on TiO₂ exposed to visible light radiation, *Environ. Sci. Technol.*, Vol. 34, (2000), 3982-3990.
- a. Houas, H.Lachheb, M.Ksibi, E.Elaloui, C.Guillard, J.M.Herrmann, Photocatalytic degradation pathway of methylene blue in water, *Appl. Catal. B Env.*, Vol. 31, (2001),pp. 145-157.

- [38] Y.F.Chen,C.Y. Lee,M.Y. Yeng, H.T. Chiu, The effect of calcination temperature on the crystallinity of TiO₂nanopowders, J. Cryst. Growth., Vol. 247, (2003) ,pp. 363-370.
- [39] S.Munusamy,R.S.L.Aparna,R.G.S.V.Prasad,A.R.Phani , Photocatalytic effect of TiO₂ and the effect of dopants on degradation of Pharmaceutical dye (Sunset Yellow), J. *Green Sci. Technol.* (in press). (2012)
- [40] K.Dai,H. Chen,T. Peng,D. Ke,H. Yi, Photocatalytic degradation of methyl orange in aqueous suspension of mesoporous titania nanoparticles, Chemosphere,Vol. 69, (2007),1361-1367.

